



This document is the translation of the French certificate n° 17-01511 L on the 2<sup>nd</sup> June, 2017 delivered by IFTH.

**MATERIAL REACTION TO FIRE CLASSIFICATION  
REPORT PREPARED IN COMPLIANCE WITH AMENDED 5 OF THE FRENCH HOME OFFICE  
REGULATION DATED NOVEMBER 21<sup>ST</sup>, 2002 (OFFICIAL GAZETTE DATED DECEMBER 31, 2002)**

Valid five years from issue date

**CERTIFICATE N° 17-01511 L**

And appendices of 6 pages

**MATERIAL presented by :** INDETEX SA  
TORKONJESTRAAT 21C  
C-8510 KORTRIJK-MARKE BELGIUM  
BELGIUM

**TRADE NAME :** PORTO (738) - PESCI (732) - PALOMA (735) - PEGASO (730)

**BRIEF DESCRIPTION :** Fabric made of 100% inherent flame retardant polyester fibers  
Measured surface weight : around 20 to 80 g/m<sup>2</sup>  
Measured thickness : around 0.1 mm  
Colours : white and off-white

**TEST REPORT :** N° 17-01511 E1-V1 on the 2<sup>nd</sup> June 2017

**TESTS :** Electrical burner test  
Flame persistence test  
Dripping test

**CLASSIFICATION :** **M 1**

Valid for any application with the exception of the stuffed seats regulated by the article AM18 for buildings receiving public

**CLASSIFICATION DURATION (article 5 of appendix 2):** unlimited unless otherwise specified

given the criteria resulting from the tests described in the enclosed test report.

The classification indicated does not mean that materials marketed comply with the test samples and must not be considered as a qualification certificate as defined by French law dated June 3, 1994.

N.B.: Only integral copies of this document may be made by photocopying the classification report and/or the classification report and enclosed test report.

Issued in Lyon, France, on the 2<sup>nd</sup> June 2017

Head of Quality Management Test and trials  
Jean-Marc ORAISON

**cofrac**  
ACCREDITATION  
N° 1-0101  
PORTÉE  
COMMUNIQUÉE  
SUR DEMANDE  
**ESSAIS**



Ecully, 02/06/2017

INDETEX SA  
Mr DEBIE Olivier  
TORKONJESTRAAT 21C  
C-8510 KORTRIJK-MARKE BELGIUM  
BELGIQUE

IFTH reference : DL170405-027

**TEST REPORT N° 17-01511 E1 - V1**

The copie of this document is only authorised in its integral version

**PURPOSE OF THE REQUEST**

Customer reference :

Date of request : 05/04/2017

Purchase order : signé

Samples supplied on : 03/05/2017

Subject :

N° CE/CL :

N° CQ :

**SAMPLE(S) REFERENCE(S)**

17-01511-001 : PORTO (738) / PESCI (732) / PALOMA (735) / PEGASO (730)

## DETAILS OF RESULTS

17-01511-001

PORTO (738) / PESCI (732) / PALOMA (735) / PEGASO (730)

Buildings material - Reaction to fire - Electrical burner test  
NF P 92-503 (1995)

Test carried out according to COFRAC accreditation

## PROCESS CONDITIONS

Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days

Number of tested specimens : 4

Testing location : Ecully

Date of the test : 23/05/2017

## RESULTS

## Specimen 1

specimen tested	PORTO (738)
Direction tested	Warp direction
Other informations:	White
Times of ignitions (in s)	/
Durations of ignitions (in s)	/
Fall of not ardent drops	No
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	235
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

## Specimen 2

specimen tested	PESCI (732)
Direction tested	Weft direction
Other informations:	Off white
Times of ignitions (in s)	/
Durations of ignitions (in s)	/
Fall of not ardent drops	No
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	181
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

## Specimen 3

specimen tested	PESCI (732)
Direction tested	Warp direction
Other informations:	Off white
Times of ignitions (in s)	/
Durations of ignitions (in s)	/
Fall of not ardent drops	No
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	170
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

## Specimen 4

specimen tested	PEGASO (730)
Direction tested	Weft direction
Other informations:	White
Times of ignitions (in s)	/

---

Durations of ignitions (in s)	/
Fall of not ardent drops	No
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	190
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No
<b>Average of carbonized lengthes (in mm)</b>	<b>194</b>
<b>Average of carbonized widthes between 45 and 60 cm (in mm)</b>	<b>/</b>
<b>Drilling by fusion without ignition or with ignition less than 5 s</b>	<b>Yes</b>
<b>Maximum duration of ignition (in s)</b>	<b>0</b>
<b>Fall of ardent drops or fragment fired</b>	<b>No</b>
<b>Afterglow with spread on more than 25 cm (in mm)</b>	<b>No</b>

**DETAILS OF RESULTS**

17-01511-001

PORTO (738) / PESCI (732) / PALOMA (735) / PEGASO (730)

Buildings material - Reaction to fire - Flame persistence test and speed of the spread of flame.  
NF P 92-504 (1995)

Test carried out according to COFRAC accreditation

**PROCESS CONDITIONS**
*Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days*
*Number of tested specimens : 4*
*Testing location : Ecully*
*Date of the test : 23/05/2017*
**RESULTS**
**Specimen 1**

Specimen tested	PORTO (738)
Direction tested	Warp direction
Other informations:	White
Durations of inflammations (in s)	0/0/0/0/0/0/0/0/0
Fall of not ardent drops	No
Fall of ardent drops	No

**Specimen 2**

Specimen tested	PALOMA (735)
Direction tested	Weft direction
Other informations:	Off white
Durations of inflammations (in s)	0/0/0/0/0/0/0/0/0
Fall of not ardent drops	No
Fall of ardent drops	No

**Specimen 3**

Specimen tested	PALOMA (735)
Direction tested	Warp direction
Other informations:	Off white
Durations of inflammations (in s)	0/0/0/0/0/0/0/0/0
Fall of not ardent drops	No
Fall of ardent drops	No

**Specimen 4**

Specimen tested	PEGASO (730)
Direction tested	Weft direction
Other informations:	White
Durations of inflammations (in s)	0/0/0/0/0/0/0/0/0
Fall of not ardent drops	No
Fall of ardent drops	No

<b>Maximum duration of ignition (in s)</b>	<b>0</b>
<b>Fall of ardent drops or fragment fired</b>	<b>No</b>

**DETAILS OF RESULTS**

17-01511-001

PORTO (738) / PESCI (732) / PALOMA (735) / PEGASO (730)

**Buildings material - Reaction to fire - Dripping test.  
NF P 92-505 (1995)**

Test carried out according to COFRAC accreditation

**PROCESS CONDITIONS**

Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days

Number of tested specimens : 4

Testing location : Ecully

Date of the test : 23/05/2017

**RESULTS**

**Specimen 1**

Specimen tested	PORTO (738)
Other informations:	White
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

**Specimen 2**

Specimen tested	PALOMA (735)
Other informations:	Off white
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

**Specimen 3**

Specimen tested	PESCI (732)
Other informations:	Off white
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

**Specimen 4**


Specimen tested	PEGASO (730)
Other informations:	White
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

<b>At least one sample ignited cotton</b>	<b>No</b>
---	-----------

## SAMPLE DESCRIPTION ANNOUNCED BY THE CLIENT

17-01511-001	PORTO (738) / PESCI (732) / PALOMA (735) / PEGASO (730)
Composition	Tissu 100% polyester ignifugé dans la masse / 100% inherent flame retardant polyester fabric
Measured Mass per unit area	De/From 20g/m <sup>2</sup> à/to 80g/m <sup>2</sup>
Measured Thickness	Environ/About 0,1
Color	Porto 730 col 10 (Blanc/White) - Pegaso 730 col 10 (Blanc/White) - Paloma 735 col 15 (Blanc cassé/Off White)
Test requested by	INDETEX
Name and address of the producer	INDETEX 58 Rue du Mont Gallois 7700 MOUSCRON, Belgique
Name and address of the supplier	INDETEX 58 Rue du Mont Gallois 7700 MOUSCRON, Belgique

Cedric ROSSARD  
UAP Manager



I.F.T.H. service clientèle  
Avenue Guy de Collongue - 69134 ECULLY CEDEX  
FRANCE  
SIRET 433 430 832 00017

Number of pages : 6 Appendices : 0

Portée disponible sur :  
www.cofrac.fr



Accréditations N°:  
Ecully 1-0101  
Saint-Prisat-est-Jarez 1-5688

If test reports, interpretation reports, comments, advice or observations are translated into a foreign language, only the version in French is valid.

« The uncertainty associated to the result was not explicitly taken in consideration to declare the conformity to the specification. Conformities are given only for the results associated to a specification. Results of this test report are only valid for specimens subjected to testing at IFTH. »

\* End of report \*