



This document is the translation of the French certificate n°18-00994 L on the May 16<sup>th</sup>, 2018 delivered by IFTH.

**MATERIAL REACTION TO FIRE CLASSIFICATION**  
**REPORT PREPARED IN COMPLIANCE WITH AMENDED 5 OF THE FRENCH HOME OFFICE**  
**REGULATION DATED NOVEMBER 21<sup>ST</sup>, 2002 (OFFICIAL GAZETTE DATED DECEMBER 31, 2002)**

Valid five years from issue date

**CERTIFICATE N°18-00994 L**

And appendices of 6 pages

**MATERIAL presented by:** INDETEX SA  
58 RUE DU MONT GALLOIS  
7700 MOUSCRON  
BELGIQUE

**TRADE NAME:** MONTECARLO

**BRIEF DESCRIPTION:** Fabric 100 % inherent fire resistant polyester  
Nominal surface weight: 335 g/m<sup>2</sup>  
Nominal thickness: 0.7 mm  
Colours: various

**TEST REPORT:** N°18-00994 E1-V1 on the May 16<sup>th</sup>, 2018

**TESTS:** Electrical burner test  
Flame persistence test  
Dripping test

**CLASSIFICATION:**

**M 1**

**CLASSIFICATION DURATION (article 5 of appendix 2):** unlimited unless otherwise specified

given the criteria resulting from the tests described in the enclosed test report.

The classification indicated does not mean that materials marketed comply with the test samples and must not be considered as a qualification certificate as defined by French law article L.433-3 n°2016-301 dated March 14<sup>th</sup>, 2016.

N.B.: Only integral copies of this document may be made by photocopying the classification report and/or the classification report and enclosed test report.

Issued in Lyon, France, on the May 16<sup>th</sup>, 2018

Sophie GUINAMAND  
Engineer Tests and Trials

Jean-Marc ORAISON  
In charge of Fire Regulation



Ecully, 16/05/2018

INDETEX SA  
Mr DEBIE OLIVIER  
58 RUE DU MONT GALLOIS  
7700 MOUSCRON  
BELGIQUE

IFTH reference : DL180323-009

**TEST REPORT N° 18-00994 E1 - V1**

The copie of this document is only authorised in its integral version

**PURPOSE OF THE REQUEST**

Customer reference : Classement M : MONTECARLO

Date of request : 23/03/2018

Purchase order : commande validée

Samples supplied on : 06/04/2018

Subject :

N° CE/CL :

N° CQ :

**SAMPLE(S) REFERENCE(S)**

18-00994-001 : MONTECARLO

**DETAILS OF RESULTS**

18-00994-001

MONTECARLO

**Buildings material - Reaction to fire - Electrical burner test  
NF P 92-503 (1995)**

Test carried out according to COFRAC accreditation

**PROCESS CONDITIONS**

Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days

Number of tested specimens : 4

Testing location : Ecully

Date of the test : 27/03/2018

**RESULTS**

Specimen 1

specimen tested	Beige
Side tested	Front side
Direction tested	Warp direction
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	162
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

Specimen 2

specimen tested	Beige
Side tested	Front side
Direction tested	Weft direction
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	120
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

Specimen 3

specimen tested	Blue
Side tested	Back side
Direction tested	Warp direction
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	162
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

Specimen 4

specimen tested	White
Side tested	Back side
Direction tested	Weft direction
Times of ignitions (in s)	/

---

Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	176
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No
<b>Average of carbonized lengthes (in mm)</b>	<b>155</b>
<b>Average of carbonized widthes between 45 and 60 cm (in mm)</b>	<b>/</b>
<b>Drilling by fusion without ignition or with ignition less than 5 s</b>	<b>Yes</b>
<b>Maximum duration of ignition (in s)</b>	<b>0</b>
<b>Fall of ardent drops or fragment fired</b>	<b>No</b>
<b>Afterglow with spread on more than 25 cm (in mm)</b>	<b>No</b>

**DETAILS OF RESULTS**

18-00994-001

MONTECARLO

**Buildings material - Reaction to fire - Flame persistence test and speed of the spread of flame.  
NF P 92-504 (1995)**

Test carried out according to COFRAC accreditation

**PROCESS CONDITIONS**

Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days

Number of tested specimens : 4

Testing location : Ecully

Date of the test : 27/03/2018

**RESULTS**

Specimen 1

Specimen tested	White
Side tested	Front side
Direction tested	Warp direction
Durations of inflammations (in s)	0/0/0/0/0/0/0/0/0
Fall of not ardent drops	No
Fall of ardent drops	No

Specimen 2

Specimen tested	White
Side tested	Front side
Direction tested	Weft direction
Durations of inflammations (in s)	0/0/0/0/0/0/0/0/0
Fall of not ardent drops	No
Fall of ardent drops	No

Specimen 3

Specimen tested	Beige
Side tested	Back side
Direction tested	Warp direction
Durations of inflammations (in s)	0/0/0/0/0/0/0/0/0
Fall of not ardent drops	No
Fall of ardent drops	No

Specimen 4

Specimen tested	Blue
Side tested	Back side
Direction tested	Weft direction
Durations of inflammations (in s)	0/0/0/0/0/0/0/0/0
Fall of not ardent drops	No
Fall of ardent drops	No

Maximum duration of ignition (in s)	0
Fall of ardent drops or fragment fired	No

## DETAILS OF RESULTS

18-00994-001

MONTECARLO

Buildings material - Reaction to fire - Dripping test.  
NF P 92-505 (1995)

Test carried out according to COFRAC accreditation

## PROCESS CONDITIONS

Conditioning of specimens before tests :  $(23 \pm 2)^\circ \text{C}$  and  $(50 \pm 5) \% \text{RH}$  during minimum 7 days

Number of tested specimens : 4

Testing location : Ecully

Date of the test : 27/03/2018

## RESULTS

## Specimen 1

Specimen tested	White
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

## Specimen 2

Specimen tested	White
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

## Specimen 3

Specimen tested	Beige
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

## Specimen 4

Specimen tested	Blue
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No


At least one sample ignited cotton

No

## SAMPLE DESCRIPTION ANNOUNCED BY THE CLIENT

18-00994-001	MONTECARLO
Composition	Tissu 100 % polyester ignifugé dans la masse / Fabric 100 % inherent fire resistant polyester
Mass per unit area	335 g/m <sup>2</sup>
Thickness	0.70 mm
Color	Blanc/white 1006 ; Beige 1009 ; Bleu/blue 1028
Test requested by	INDETEX NV
Name and address of the producer	INDETEX NV Rue du Mont-Gallois B-7700 MOUCRON (Belgique)
Name and address of the supplier	INDETEX NV Rue du Mont-Gallois B-7700 MOUCRON (Belgique)

Cedric ROSSARD  
UAP Manager



## I.F.T.H. service clientèle

Avenue Guy de Collongue - 69134 ECULLY CEDEX  
FRANCE

SIRET 433 430 832 00017



Portée disponible sur :  
[www.cofrac.fr](http://www.cofrac.fr)  
Accréditations N°:  
Ecully 1-0101  
Saint-Priest-en-Jarez 1-5688

Number of pages : 6 Appendices : 0

If test reports, interpretation reports, comments, advice or observations are translated into a foreign language, only the version in French is valid.

« The uncertainty associated to the result was not explicitly taken in consideration to declare the conformity to the specification. Conformities are given only for the results associated to a specification. *Results of this test report are only valid for specimens subjected to testing at IFTH.* »

\* End of report \*