



**Indetex nv**  
**Dhr. Jan De Praeter**  
**Rue du Mont Gallois 58**  
**7700 MOUSCRON**

**Your notice of**  
 05-11-2019

**Your reference**

**Date**  
 05-12-2019

**Analysis Report 19.06284.02**

Required tests :

**EN 13773 (2003)**

Identification number	Information given by the client	Date of receipt
T1924302	VICENZE / ARIETE	05-11-2019



**Gina Créelle**  
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T1924302 - VICENZE / ARIETE**

**Washing and drying**

Date of ending the test 07-11-2019  
Standard used ISO 10528 (1995)

Deviation from the standard -  
Apparatus Wascator FOM 71 (type A)  
Used detergent IEC detergent  
Washing method and temperature 66- 30°  
Drying method A = Line dry  
Number of washing cycles 5

Sample generated: T1924302\_01d

**Reference:** T1924302\_01d - VICENZE / ARIETE

**Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.**

Date of ending the test 20-11-2019  
Standard used EN 1101 (1995) + A1 (2005)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%


Ignition Bottom edge

The test specimens have been washed 5 times instead of 12 times.

**Length**

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
No ignition within 20 s



### Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
No ignition within 20 s

Reference: T1924302\_01d - VICENZE / ARIETE

**Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.**

Date of ending the test 05-12-2019  
Standard used EN 13772 (2011)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have been washed 5 times instead of 12 times.

**Length**

	Face A	Face B	Face A	Face A
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	145	125	145	150
Flaming debris	no	no	no	no

**Width**

	Face A	Face B	Face A	Face A
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	145	125	150	150
Flaming debris	no	no	no	no

**Classification in accordance with EN 13773 Class 1**