

**PROCES-VERBAL DE CLASSEMENT DE REACTION AU FEU
D'UN MATERIAU PREVU A L'ARTICLE 5
DE L'ARRÊTE DU 21 NOVEMBRE 2002**

Valable 5 ans à partir de la date de délivrance

PROCES-VERBAL N° 19-01221 L

et 1 annexe de 6 pages

MATERIAU présenté par : INDETEX SA
58 rue du Mont Gallois
7700 MOUSCRON
BELGIQUE

MARQUE COMMERCIALE : VEROLI

DESCRIPTION SOMMAIRE : Tissu 100% polyester ignifugé dans la masse
Masse surfacique nominale : 295 g/m²
Epaisseur mesurée : environ 0.60 mm
Coloris : Divers

RAPPORT D'ESSAI : N° 19-01221 E1-V1 du 2 Mai 2019

NATURE DES ESSAIS : Brûleur électrique
Propagation de flamme
Essai pour matériaux fusibles

CLASSEMENT :

M 1

DURABILITE du classement (Article 5 de l'annexe 2) : non limitée a priori.

Compte tenu des critères résultant des essais décrits dans le rapport d'essai annexé.

Ce document atteste uniquement des caractéristiques de l'échantillon soumis aux essais et ne préjuge pas des caractéristiques de produits similaires. Il ne constitue donc pas une certification de produits au sens de l'article L.433-3 l'Ordonnance n°2016-301 du 14 mars 2016 relative au code de la consommation

NOTA : Sont seules autorisées les reproductions intégrales et par photocopie du présent procès-verbal de classement ou de l'ensemble procès-verbal de classement et rapport d'essai annexé.

A Lyon, le 2 Mai 2019

Guinamand

Sophie GUINAMAND
Ingénieur Tests et Essais

Ecully, 02/05/2019

INDETEX SA
Mr DEBIE OLIVIER
58 RUE DU MONT GALLOIS
7700 MOUSCRON
BELGIQUE

IFTH reference : DL190404-005

TEST REPORT N° 19-01221 E1-V1

The copie of this document is only authorised in its integral version

PURPOSE OF THE REQUEST

Customer reference : VEROLI

Date of request : 04/04/2019

Purchase order : devis signé 04/04

Samples supplied on : 16/04/2019

Subject : Classement M

N° CE/CL :

N° CQ :

SAMPLE(S) REFERENCE(S)

19-01221-001 : VEROLI

DETAILS OF RESULTS

19-01221-001

VEROLI

**Buildings material - Reaction to fire - Electrical burner test
NF P 92-503 (1995)**

Test carried out according to COFRAC accreditation

PROCESS CONDITIONS

Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days

Number of tested specimens : 4

Testing location : Ecully

Date of the test : 30/04/2019

RESULTS

Specimen 1

specimen tested	1008
Direction tested	Warp direction
Other informations:	Grey
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	120
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

Specimen 2

specimen tested	1008
Direction tested	Weft direction
Other informations:	Grey
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	130
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

Specimen 3

specimen tested	1005
Direction tested	Warp direction
Other informations:	White
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	120
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No

Specimen 4

specimen tested	1002
Direction tested	Weft direction
Other informations:	Beige
Times of ignitions (in s)	/

Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Fall of fragment fired	No
Carbonized length (in mm)	160
Carbonized width between 45 and 60 cm (in mm)	/
Afterglow with spread on more than 25 cm (in mm)	No
Average of carbonized lengths (in mm)	133
Average of carbonized widths between 45 and 60 cm (in mm)	/
Drilling by fusion without ignition or with ignition less than 5 s	Yes
Maximum duration of ignition (in s)	0
Fall of ardent drops or fragment fired	No
Afterglow with spread on more than 25 cm (in mm)	No

DETAILS OF RESULTS

19-01221-001	VEROLI
--------------	--------

**Buildings material - Reaction to fire - Flame persistence test and speed of the spread of flame.
NF P 92-504 (1995)**

Test carried out according to COFRAC accreditation

PROCESS CONDITIONS

Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days
Number of tested specimens : 4
Testing location : Ecully
Date of the test : 30/04/2019

RESULTS

Specimen 1	Specimen tested Direction tested Other informations: Durations of inflammations (in s) Fall of not ardent drops Fall of ardent drops	1005 Warp direction White 0/0/0/0/0/0/0/0/0 Yes No
Specimen 2	Specimen tested Direction tested Other informations: Durations of inflammations (in s) Fall of not ardent drops Fall of ardent drops	1005 Weft direction White 0/0/0/0/0/0/0/0/0 Yes No
Specimen 3	Specimen tested Direction tested Other informations: Durations of inflammations (in s) Fall of not ardent drops Fall of ardent drops	1002 Warp direction Beige 0/0/0/0/0/0/0/0/0 Yes No
Specimen 4	Specimen tested Direction tested Other informations: Durations of inflammations (in s) Fall of not ardent drops Fall of ardent drops Maximum duration of ignition (in s) Fall of ardent drops or fragment fired	1008 Weft direction Grey 0/0/0/0/0/0/0/0/0 Yes No 0 No

DETAILS OF RESULTS

19-01221-001

VEROLI

Buildings material - Reaction to fire - Dripping test.
NF P 92-505 (1995)

Test carried out according to COFRAC accreditation

PROCESS CONDITIONS

Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days

Number of tested specimens : 4

Testing location : Ecully

Date of the test : 30/04/2019

RESULTS

Specimen 1

Specimen tested	1002
Other informations:	Beige
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

Specimen 2

Specimen tested	1002
Other informations:	Beige
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

Specimen 3

Specimen tested	1008
Other informations:	Grey
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

Specimen 4


Specimen tested	1005
Other informations:	White
Times of ignitions (in s)	/
Durations of ignitions (in s)	0
Fall of not ardent drops	Yes
Fall of ardent drops	No
Ignition of cotton	No

At least one sample ignited cotton	No
-------------------------------------------	-----------

SAMPLE DESCRIPTION ANNOUNCED BY THE CLIENT

19-01221-001	VEROLI
Composition	Tissu 100% polyester ignifugé dans la masse / 100% inherent fire resistant polyester fabric
Mass per unit area	295 g/m ²
Measured Thickness	Environ/About 0,60 mm
Color	1002 (Beige) ; 1008 (Gris/Grey) ; 1005 (Blanc/White)
Test requested by	INDETEX NV
Name and address of the producer	INDETEX NV RUE DU MONT-GALLOIS 58 B-7700 MOUSCRON (BELGIUM)
Name and address of the supplier	INDETEX NV RUE DU MONT-GALLOIS 58 B-7700 MOUSCRON (BELGIUM)

Cedric ROSSARD
Laboratory Manager



I.F.T.H. service clientèle
Avenue Guy de Collongue - 69134 ECULLY CEDEX
FRANCE
SIRET 433 430 832 00017



Portée disponible sur :
www.cofrac.fr
Accréditations N°:
Ecully 1-0101
Saint-Priest-en-Jarez 1-5688

Number of pages : 6 Appendices : 0

If test reports, interpretation reports, comments, advice or observations are translated into a foreign language, only the version in French is valid.

« The uncertainty associated to the result was not explicitly taken in consideration to declare the conformity to the specification. Conformities are given only for the results associated to a specification. Results of this test report are only valid for specimens subjected to testing at IFTH. »

* End of report *