

Centexbel  
Mevr. Hilde Beeckman  
Technologiepark 7  
9052 ZWIJNAARDE



Company: Dhr. Philippe Debie - Indetex nv Marke

Your notice of  
14-01-2015

Your reference

Date  
30-01-2015

**Analysis Report 15.00157.03**

Required tests :

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 7      Fire Test Procedures - Test for vertically supported textiles and films

Identification number	Information given by the client	Date of receipt
T1500702	Pearl/Lira/lupo	14-01-2015

Gina Créelle

Order responsible

This report runs to 5 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

VAT BE 0459.218.289

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-GENT  
Technologiepark 7  
BE-9052 Zwijnaarde  
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55  
gent@centexbel.be

CENTEXBEL-VERVIERS  
Avenue du Parc 38  
BE-4650 Herve (Chaîneux)  
Tel. + 32 87 32 24 30 Fax + 32 87 34 05 18  
chaîneux@centexbel.be

Reference: T1500702 - Pearl/Lira/lupo

Fire Test Procedures - Test for vertically supported textiles and films

Date of ending the test 29-01-2015  
 Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 7  
 Deviation from the standard -  
 Conditioning 20°C, relative humidity 65%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 5 - 15

Weight (g/m<sup>2</sup>) 284

A = front - B = back

**Face A**

**Determination of the test conditions.**

Length

	Surface A		Edge	
	5	15	5	15
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Afterglow (s)	0	0	0	0
Surface flash	no	no	no	no
Side edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	28	32	19	35

No sustained ignition : testing continued under conditions showing the greatest damaged length.

## Width

	Surface A		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Afterglow (s)	0	0	0	0
Surface flash	no	no	no	no
Side edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	25	36	43	40

No sustained ignition : testing continued under conditions showing the greatest damaged length.

**Worst testing conditions**

Length      Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Afterglow (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Side edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	35	52	71	43	32	47

Width      Edge - flame application time 5 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Afterglow (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Side edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	43	42	31	37	39	38

**Face B****Determination of the test conditions.**

## Length

	Surface B		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Afterglow (s)	0	0	0	0
Surface flash	no	no	no	no
Side edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	30	35	40	53

No sustained ignition : testing continued under conditions showing the greatest damaged length.

## Width

	Surface B		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Afterglow (s)	0	0	0	0
Surface flash	no	no	no	no
Side edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	26	34	26	44

No sustained ignition : testing continued under conditions showing the greatest damaged length.

**Worst testing conditions**

Length Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Afterglow (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Side edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	53	40	45	69	50	51

Width Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Afterglow (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Side edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	44	68	41	50	38	48

***Criteria for curtains and drapes***

1. Afterflame time  $\leq 5$ s for any specimen tested with face ignition.
2. No flame propagation to the edges for any specimen tested with face ignition..
3. No ignition of the cotton wool for any specimen.
4. Average char length  $\leq 150$  mm in any of the baches tested with face or edge ignition.
5. No occurrence of a surface flash more than 100 mm from the point of ignition.

Remark: If the test for length and/or width is carried out with edge ignition, the results obtained through the edge application are considered for the purposes of the criteria 1 and 2.

**The fabric passes the proposed criteria for curtains and drapes.**