

COSY

Dim out FR - 150 cm



30°C

6°C




0°C

20°C



0610



0603




0601



0607




0605



0604



0612




0602



0619




0614




0615



0616




0618



0609



0620



0621




0606



0611




0622



0623



0617



0608

COSY

DIM OUT

COSY

Dim out FR - 150 cm

		CHARACTERISTICS	EIGENSCHAPPEN	PROPRIÉTÉS	EIGENSCHAFTEN
	Dim out	Transparency level	Transparantie	Transparence	Transparenz
	100% Pes FR	Composition	Samenstelling	Composition	Zusammensetzung
	330 gr/m ²	Weight	Gewicht	Poids	Gewicht
	0,55 mm	Thickness	Dikte	Epaisseur	Dicke
	150 cm	Max. width	Max. breedte	Largeur max.	Max. Nutzbreite
	M1, IMO, BS5867, NFPA701	Flame retardant	Brandvrije Norm	Classement au feu	Schwerentflammbarkeit
	4 - 5 (ISO 105 B02)	Light fastness	Lichtechtheid	Résistance à la lumière	Lichtechtheit
	warp: 338/inch - 75D Pes FR weft: 110/inch - 450D Pes FR + 300D Pes FR	Weaving Construction	Weef Constructie	Construction tissage	Webkonstruktion
	3-4 (ISO 105 C04)	Colour fastness after washing	Kleurechtheid bij het wassen	Solidité des couleurs après lavage	Farbechtheit beim Waschen
		Washing instructions	Wasvoorschriften	Nettoyage	Pflegehinweis
	1%-2% (30°C) (EN ISO 5070 & EN ISO 6330)	Approx. shrinking possible	Mogelijke krimp	Rétrécissement possible	Ca. Schrumpfung möglich
	$\alpha_w = 0,85$ (EN ISO 354/EN ISO 11654)	Sound absorption	Geluidsabsorptie	Absorption du son	Schallabsorption
		Applications - end-use	Toepassingen - eindgebruik	Applications - usage final	Anwendungen - Endverwendung
		Direction of use	Gebruiksrichting	Sens d'utilisation	Gebrauchsanweisung
	certificate available - certificaat beschikbaar - certificat disponible - zertifikat verfügbar	Sustainability	Duurzaamheid	Durabilité	Nachhaltigkeit
	not available - niet van toepassing - non disponible - nicht verfügbar	Recycled Yarns	Gerecycleerde garens	Fils recyclés	Recycelte Garne

THERMAL COMFORT (EN 14501)

0°C 20°C BENEFIT * 44%	Thermal comfort winter Thermisch comfort winter Confort thermique hiver Thermische Behaglichkeit Winter
30°C 6°C BENEFIT * 33%	Thermal comfort summer Thermisch comfort zomer Confort thermique été Thermische Behaglichkeit Sommer

ACOUSTIC COMFORT

-20% BENEFIT * 23% α_w 0 0,85 1	Sound insulation Akoestisch comfort Isolation acoustique Schalldämmung
--	---

VISUAL COMFORT (EN 14501)

-50% -100% 0 1 2 3	Black out level Verduisteringsniveau Contrôle de l'opacité Verdunklungsgrad
0 1 2 3 4	Glare control Afscherming tegen schittering Contrôle de l'éblouissement Blendschutz
0 1 2 3 4	Privacy Privacy Intimité de nuit Privacy
0 1 2 3 4	Visual contact with outside world Visueel contact met buitenwereld Contact visuel avec l'extérieur Sichtcontact met der Außenwelt

* Max. expected benefit with single glazing / Max. verwachte winst bij enkele beglazing / Bénéfice max. attendu avec simple vitrage / Max. zu erwartender Nutzen bei einfach verglasten Fenstern